

In re Patent Application of:  
**CHAI ET AL.**  
Serial No. 10/803,467  
Confirmation No. 5525  
Filed: MARCH 18, 2004

---

In the Claims:

1. (Original) A method for making at least one semiconductor device comprising:  
    providing a sacrificial growth substrate comprising Lithium Aluminate ( $\text{LiAlO}_2$ );  
    forming at least one semiconductor layer comprising a Group III nitride adjacent the sacrificial growth substrate;  
    attaching a mounting substrate adjacent the at least one semiconductor layer opposite the sacrificial growth substrate; and  
    removing the sacrificial growth substrate.
2. (Original) A method according to Claim 1 further comprising adding at least one contact onto a surface of the at least one semiconductor layer opposite the mounting substrate.
3. (Original) A method according to Claim 2 further comprising dividing the mounting substrate and at least one semiconductor layer into a plurality of individual semiconductor devices.
4. (Original) A method according to Claim 3 further comprising bonding the mounting substrate of each individual semiconductor device to a heat sink.
5. (Original) A method according to Claim 4 wherein the heat sink comprises copper (Cu) block.

In re Patent Application of:  
**CHAI ET AL.**  
Serial No. 10/803,467  
Confirmation No. 5525  
Filed: **MARCH 18, 2004**

---

6. (Original) A method according to Claim 1 wherein removing comprises mechanical grinding and wet etching the sacrificial growth substrate.

7. (Original) A method according to Claim 6 wherein the mounting substrate is resistant to the wet etching.

8. (Original) A method according to Claim 6 further comprising protecting at least portions of the mounting substrate during wet etching.

9. (Original) A method according to Claim 1 wherein the sacrificial growth substrate comprises single crystal  $\text{LiAlO}_2$ .

10. (Original) A method according to Claim 1 wherein the at least one semiconductor layer comprises at least one single crystal gallium nitride (GaN) layer.

11. (Original) A method according to Claim 1 wherein attaching the mounting substrate comprises:

forming an adhesion layer on the at least one semiconductor layer; and

bonding the adhesion layer to the mounting substrate.

In re Patent Application of:  
**CHAI ET AL.**  
Serial No. **10/803,467**  
Confirmation No. **5525**  
Filed: **MARCH 18, 2004**

---

12. (Original) A method according to Claim 11 wherein the adhesion layer comprises at least one of nickel (Ni) and gold (Au).

13. (Original) A method according to Claim 11 wherein the mounting substrate comprises at least one of copper (Cu), silver (Ag), gold (Au), aluminum (Al), chromium (Cr), nickel (Ni), titanium (Ti), molybdenum (Mo), tungsten (W), zirconium (Zr), platinum (Pt), palladium (Pd), and silicon (Si).

14. (Original) A method according to Claim 1 wherein forming the at least one semiconductor layer comprises doping the at least one semiconductor layer.

15. (Original) A method according to Claim 1 further comprising forming a buffer layer between the sacrificial growth substrate and the at least one semiconductor layer; and wherein removing the sacrificial growth substrate further comprises removing the buffer layer.

16. (Original) A method according to Claim 1 wherein the at least one semiconductor layer has an m-plane (10 $\bar{1}$ 0) orientation.

17. (Original) A method according to Claim 1 wherein the at least one semiconductor layer has a thickness of less than about 10  $\mu\text{m}$ .

In re Patent Application of:  
**CHAI ET AL.**  
Serial No. 10/803,467  
Confirmation No. 5525  
Filed: MARCH 18, 2004

---

18. (Original) A method according to Claim 1 wherein the at least one semiconductor layer emits light upon being electrically biased.

19. (Original) A method for making a plurality of semiconductor devices comprising:

providing a sacrificial growth substrate comprising Lithium Aluminate ( $\text{LiAlO}_2$ );

forming at least one semiconductor layer comprising a Group III nitride adjacent the sacrificial growth substrate;

attaching a mounting substrate adjacent the at least one semiconductor layer opposite the sacrificial growth substrate, the mounting substrate comprising at least one of a metal and silicon;

removing the sacrificial growth substrate using mechanical grinding and wet chemical etch;

forming a plurality of contacts on the at least one semiconductor layer opposite the mounting substrate; and

dividing the mounting substrate and at least one semiconductor layer into a plurality of individual semiconductor devices.

20. (Original) A method according to Claim 19 further comprising bonding the mounting substrate of each individual semiconductor device to a heat sink.

21. (Original) A method according to Claim 19 wherein the mounting substrate is resistant to the wet etching.

In re Patent Application of:  
**CHAI ET AL.**  
Serial No. **10/803,467**  
Confirmation No. **5525**  
Filed: **MARCH 18, 2004**

---

22. (Original) A method according to Claim 19 further comprising protecting at least portions of the mounting substrate during wet etching.

23. (Original) A method according to Claim 19 wherein the sacrificial growth substrate comprises single crystal  $\text{LiAlO}_2$ .

24. (Original) A method according to Claim 19 wherein the at least one semiconductor layer comprises at least one single crystal gallium nitride (GaN) layer.

25. (Original) A method according to Claim 19 wherein attaching the mounting substrate comprises:

forming an adhesion layer on the at least one semiconductor layer; and

bonding the adhesion layer to the mounting substrate.

26. (Original) A method according to Claim 19 wherein forming the at least one semiconductor layer comprises doping the at least one semiconductor layer.

27. (Original) A method according to Claim 19 further comprising forming a buffer layer between the sacrificial growth substrate and the at least one semiconductor layer; and wherein removing the sacrificial growth substrate further comprises removing the buffer layer.

In re Patent Application of:

**CHAI ET AL.**

Serial No. **10/803,467**

Confirmation No. **5525**

Filed: **MARCH 18, 2004**

---

28. (Original) A method according to Claim 19 wherein the at least one semiconductor layer has an m-plane (1010) orientation.

29. (Currently amended) A method according to Claim [[1]] 19 wherein the at least one semiconductor layer emits light upon being electrically biased.

30. (Original) A method for making at least one semiconductor device comprising:

providing a sacrificial growth substrate comprising single crystal Lithium Aluminate ( $\text{LiAlO}_2$ );

forming at least one semiconductor layer comprising a Group III nitride having an m-plane (1010) orientation adjacent the sacrificial growth substrate;

attaching a mounting substrate adjacent the at least one semiconductor layer opposite the sacrificial growth substrate, the mounting substrate comprising at least one of metal and silicon; and

removing the sacrificial growth substrate.

31. (Original) A method according to Claim 30 further comprising:

adding at least one contact onto a surface of the at least one semiconductor layer opposite the mounting substrate;

dividing the mounting substrate and at least one semiconductor layer into a plurality of individual semiconductor devices; and

In re Patent Application of:

**CHAI ET AL.**

Serial No. **10/803,467**

Confirmation No. **5525**

Filed: **MARCH 18, 2004**

---

bonding the mounting substrate of each individual semiconductor device to a heat sink.

32. (Original) A method according to Claim 31 wherein removing comprises mechanical grinding and wet etching the sacrificial growth substrate; and wherein the mounting substrate is resistant to the wet etching.

33. (Original) A method according to Claim 31 wherein removing comprises mechanical grinding and wet etching the sacrificial growth substrate; and further comprising protecting at least portions of the mounting substrate during wet etching.

34. (Original) A method according to Claim 31 wherein the at least one semiconductor layer comprises at least one single crystal gallium nitride (GaN) layer.

35. (Original) A method according to Claim 31 wherein attaching the mounting substrate comprises:

forming an adhesion layer on the at least one semiconductor layer; and

bonding the adhesion layer to the mounting substrate.

36. (Original) A method according to Claim 31 further comprising forming a buffer layer between the sacrificial growth substrate and the at least one

In re Patent Application of:  
**CHAI ET AL.**  
Serial No. 10/803,467  
Confirmation No. 5525  
Filed: MARCH 18, 2004

---

semiconductor layer; and wherein removing the sacrificial growth substrate further comprises removing the buffer layer.

37. (Original) A method according to Claim 31 wherein the at least one semiconductor layer emits light upon being electrically biased.

Claims 38-49 (canceled).